SUNSTATE SANDS AUSTRALIA PTY LTD PO Box 1334, Eagle Farm BC

Level 1, 23 Chapman Place, Eagle Farm Queensland Australia 4009

Queensland Australia 4009

P +61 7 3623 4960 F +61 7 3623 4961 E mail@sunstatesands.com.au W www.sunstatesands.com.au ACN 613 628 292 ABN 99 613 628 292



## **SPECIFICATION SHEET**

Product: GS-BW Silica Sand

The below outlines the physical and chemical properties of the silica sand that will be supplied by Sunstate Sands Australia P/L.

## **Physical Properties:**

Nominated Size of Aperture (mm)	Sunstate Sands Standard Specification
0.425	Minimum 95% Passing
0.105	Minimum 95% Retained

Chemical Specification: SiO2 >99%

Al2O3 <0.12% Fe2O3 <0.030% TiO2 <0.10% Cr2O3 <0.0006%

## Note:

The above specifications for material passing the 0.425mm sieve and material retained on the 0.105mm sieve is based on one composite sample per Shipload.

Particle Size test method is conducted as per the Sunstate Sands Standard Operating Procedure (SOP) SOP-LAB 03a (PSD Particle Size Distribution of Export Sand Products).

British Standard Sieves are used.

